

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
26 June 2003 (26.06.2003)

PCT

(10) International Publication Number  
**WO 03/053101 A1**

(51) International Patent Classification<sup>7</sup>: **H05B 3/34**

(21) International Application Number: PCT/GB02/05632

(22) International Filing Date:  
12 December 2002 (12.12.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
0129968.4 14 December 2001 (14.12.2001) GB

(71) Applicant (for all designated States except US): **NEL TECHNOLOGIES LTD** [GB/GB]; Unit 7B, Westway Industrial Park, Throckley, Newcastle upon Tyne, Tyne and Wear NE15 9HW (GB).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **FERGUSON, Patrick** [GB/GB]; 22 Wenlock Drive, Preston Grange, North Shields, Tyne and Wear NE29 9HD (GB).

(74) Agent: **SANDERSON, Michael, J.**; Mewburn Ellis, York House, 23 Kingsway, London, Greater London WC2B 6HP (GB).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: FLEXIBLE ELECTRIC CIRCUIT FOR HEATING COMPRISING A METALLISED FABRIC



(57) Abstract: A flexible electric circuit, for example an electric heater, comprises a metallised fabric (14) the metal of which is photochemically etched to form the circuit (16), the fabric preferably being porous.



WO 03/053101 A1

## FLEXIBLE ELECTRIC CIRCUIT FOR HEATING COMPRISING A METALLISED FABRIC

TECHNICAL FIELD

This invention relates to flexible electric circuits, and has particular though not exclusive application to such  
5 circuits in the form of heaters and/or for incorporation in articles of clothing, footwear and fabric based electrical devices.

BACKGROUND OF THE INVENTION

The manufacture of flexible heaters by photochemical  
10 etching metal foil bonded to thin, flexible electrical insulation materials is a well established practice. Fig. 1a shows metal foil 2 bonded to an electrical insulation material 4 by the use of a suitable adhesive. The resulting heater element 6 and termination pads 8 shown in  
15 Fig. 1b are formed using conventional photochemical etching techniques. Leadwires 10 (Fig. 1c) are attached to the termination pads 8 by means of crimping, welding, soldering, conductive adhesives or other joining techniques. Electrical insulation is completed by bonding  
20 suitable insulation material 12 on top of the etched heater element as shown in Fig. 1d.

An alternative way to connect the leadwires 10 involves pre-forming openings in the top insulation layer 12 which is then bonded to the etched heater element 6.  
25 Subsequently, the termination pads 8 of the heater element

6 are connected to leadwires or connectors using crimping, welding, soldering, conductive adhesives or other joining techniques. The electrical insulation is completed by covering the heater element termination and leadwire joint  
5 with a patch of insulating material using an appropriate adhesive.

The electrical insulation materials used are in sheet form (up to 1mm thick) and are typically non-porous. Common types of flexible insulating materials used are  
10 fibre reinforced silicone rubber, polyimide and polyester. Metal sheet (typically 10µm-500µm thick) is bonded to the insulating material using an adhesive. Metals and alloys used for heater elements typically have a resistivity which has a low dependence on temperature and include, for  
15 example, copper, nichrome, nickel and stainless steel. The resistance of the heater element, and consequently the operating temperature, is controlled by changing the type of metal foil, the thickness of the metal foil or the heater element design.

20 Other types of flexible heaters available utilise different forms of heating element and include wire-wound elements, interwoven carbon fibre sheets and metallised synthetic fibre sheets such as nickel coated polyester.

It is also known to utilise metallised fabrics and  
25 similar mesh structures in the manufacture of flexible

heaters, for example as disclosed in GB 2,092,868 and DE 3210097. However such structures have total metallisation, and the electrical resistance is controlled by the metal composition, the density of application and the like.

5 SUMMARY OF THE INVENTION

It would be desirable to be able to provide a flexible electric circuit more conveniently and economically manufactured than heretofore and in which the electrical characteristics, in particular the electrical resistance,  
10 can be more easily controlled than heretofore.

According to one aspect of the present invention there is provided a flexible electric circuit comprising a metallised fabric the metal of which is photochemically etched to form the circuit.

15 It will be appreciated that such an arrangement is distinguished from the prior art in that the metal is modified by photochemical etching to provide circuit elements of chosen configuration and electrical properties.

Preferably the fabric is porous.

20 The fabric to be etched may be coated with a continuous layer of metal, for example by chemical reduction, by electro-deposition or by sputtering.

Alternatively the fabric may comprise yarns and/or fibres the individual yarns and/or fibres being  
25 encapsulated in metal prior to manufacture of the fabric.

According to a further aspect of the invention, there is provided a method of manufacturing a flexible electric circuit comprising the steps of providing a metallised fabric, and photochemically etching the metal to form the circuit.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Figs. 1a to 1d show the simplified manufacturing steps of a prior art flexible heater;

Figs. 2a to 2d show the simplified manufacturing steps of a flexible heater according to the invention;

Fig. 3 is a flow chart of the manufacturing steps of a flexible heater according to the invention;

Fig. 4 is a graph showing the log of the resistance change against track width for a standard element design for various metal foil heater elements and for the element of a heater according to the invention.

#### DESCRIPTION OF PREFERRED EMBODIMENTS

Fig. 2a shows a sheet of heat resistant polymeric mesh 14 coated with a continuous layer of metal and which forms the basis for a heater according to the invention.

The mesh 14 can take a variety of different configurations, a typical commercially available metallised woven polymeric mesh being Metalester<sup>TM</sup>. Such products are woven electroless nickel plated polyester meshes with a variety of thread thicknesses, thread spacings, type of

5

weave and weight of nickel. Threads may typically have a diameter within the range 24 to 600 microns, a thread count of between 4 and 737 per cm, and a metal coating of varying weight per square metre.

5       The fabrics may be coated with a continuous layer of metal after manufacture, for example by sputtering, by chemical reduction or by electro-deposition, which results in total encapsulation of all the threads of the mesh in metal. In an alternative mesh, the individual warp and  
10 weft threads may be metallised prior to fabric production, for example by sputtering, by chemical reduction or by electro-deposition.

      The fundamental novelty of the invention is that the metallised mesh is photochemically etched to form the  
15 heater element, a typical element 16 with termination pads 18 being shown in Fig. 2b.

      Crimp connectors or other suitable flexible substrate connection devices 20 are fixed to the termination pads 18 allowing leadwires 22 to be attached as shown in Fig. 2c,  
20 while electrical insulation is completed by bonding insulation material 24,26 to the top and bottom of the heater as shown in Fig. 2d.

      Fig. 3 shows in more detail the steps associated with the process of manufacturing an etched flexible heater from  
25 metallised woven fabric.

6

There are six main process steps involved, namely

1. design and generation of the phototool (boxes 28,30);
2. material preparation (box 32);
3. exposure and developing (box 34)
- 5 4. etching (box 36)
5. testing (box 38)
6. finishing (box 40)

The material preparation step 32 is divided into the sub-steps of:

- 10 a) cutting the metallised fabric to length (box 42);
- b) mounting the cut fabric onto a hinged frame (box 44), typically 1.5 mm thick brown styrene board, to enable the otherwise flimsy fabric to be more readily handled and to travel flat through the subsequent
- 15 multi-stage manufacturing process;
- c) cleaning the fabric with a commercial surface cleaning agent (box 46) to assist the adhesion of the photoresist - if the cleaning agent is not used, and the surface is contaminated, there is a tendency for
- 20 poor adhesion of the photoresist to the metal to be etched which can result in the etchant undercutting the photoresist and attacking the metal area which forms the required image, in turn reducing the track width and increasing the resistance of the track;

7

d) applying the photoresist (box 48) - one method of applying the photoresist is by dip-coating - i.e. immersing the fabric in a liquid photoresist to ensure a controlled application of liquid photoresist to all parts of the metallised polyester threads and to avoid undercutting of the etched track due to non-application of photoresist to parts of the threads.

The exposure and developing step 34 is divided into the sub-steps of:

- 10 a) cleaning the phototool (box 50);
  - b) exposing the photoresist to ultraviolet light (box 52), and
  - c) developing the image of the heater element on the fabric (box 54).
- 15 The etching step 36 is divided into the sub-steps of:
- a) progressively etching away the unrequired metal (box 56), and
  - b) removing the photoresist to leave the required heater element (box 58).

20 The resultant flexible heater is then tested, for example by measuring the electrical resistance, and by visual inspection (box 60).

The heater is finished by electrically insulating the porous woven metallised etched fabric, for example by bonding layers of suitable electrically insulating sheet

25



material to each side using a web consisting of low melt fibres - adhesive in the open mesh area can be minimised by applying a vacuum during lamination - or by dip-coating or paint-spraying the etched fabric with a suitable heat resistant lacquer - again the use of a vacuum after lacquer application will maximise the mesh open area. To further improve the porosity of the heater, the laminated insulating material may be a micro-porous breathable fabric or film. After lamination, the porous heater is profiled by cutting to its final shape (box 62).

The attachment of leadwires and other components such as thermal protection devices complete the product which is then re-tested for electrical performance (box 64).

Clearly the desired electrical characteristics of a heater, and in particular the heat output, will determine the particular metallised woven fabric to be used to manufacture the heater, and the width and length of the element to be photochemically etched on the fabric.

Fig. 4 shows a graph of the log of the track width in mm against the log of the resistance of the track in ohms per foot for a standard element design for each of four conventional etched foil heaters and a heater according to the invention.

The individual graphs in Fig. 4 are:

1. annealed nickel foil of 50 microns thickness;

2. annealed copper foil of 18 microns thickness;
3. annealed stainless steel (Grade 321) of 38 microns thickness;
4. annealed copper foil of 35 microns thickness;
- 5 5. Metalester <sup>TM</sup> MET 25/16 (25 g.m<sup>-2</sup>).

It can be seen that product 5, a heater according to the invention, has a resistance substantially the same as that of the stainless steel foil heater 3.

More particularly, the metal, the fibre diameter, the  
10 thickness of the metal coating, the spacing of the fibres and the element design are all taken into account to determine the required electrical characteristics.

In the above described example, the threads are typically polymeric, particularly polyester for relatively  
15 low temperature applications, although any synthetic or natural fibres may suffice as a base for the product of the invention.

In the invention the flexible electric circuit may be manufactured from fabrics incorporating yarns of the  
20 following two classes:

- (i) Continuous: mono or multi-filaments of indefinite length and including polypropylene, polyethylene, chlorofibres, viscose rayon, di- and tri-acetate, polyester, nylon, aromatic polyamide (Nomex®),  
25 poly-paraphenylene terephthalamide (Kevlar®), and

the like. Nomex® and Kevlar® are registered trademarks of E.I. du Pont de Nemours and Company.

- (ii) Staple: fibres of definite length twisted, wrapped or otherwise combined, including cotton, linen (flax), jute, wool, mohair, cashmere, angora and other speciality hair fibres, blends of varying composition thereof e.g. 60% cotton/40% polyester and the like.

Fabrics made from the above yarns or fibres (depending on the type of fabric structure) include and are not limited to the following types:

- (i) woven
- (ii) nonwoven
- (iii) knitted - includes warp and weft
- (iv) composites - laminated structures incorporating but not limited to the following: textiles, coatings, polymer films, membranes, hydrophilic and micro-porous breathable films, metals, ceramics and other materials.
- (v) pressed felts
- (vi) braids

The metal is conveniently nickel, although any resistive metal could be used.

The resultant product is thin, flexible and porous, and can be produced relatively inexpensively.

Flexible heaters according to the invention and in the form of photochemically etched metallised fabric mesh have a variety of applications, and can be incorporated in, for example, mosquito traps, wound care products such as

5 medical bandages and dressings, surgical masks and visors, motorcycle visors, sports equipment visors, outdoor and performance clothing, footwear and articles to be moulded, and can be used as aerospace de-icers. Other applications will be apparent to those skilled in the art.

10 Although described above as heaters, the invention is equally applicable to flexible electric circuits for use other than as heaters.

Such a circuit is photochemically etched from metallised woven fabric as detailed above with respect to

15 the heater element 16, and any additional components that are required are mounted thereon. Such a thin, flexible, porous electric circuit can be embedded into articles of wearable clothing and footwear, for example outdoor and performance clothing, military clothing, medical and sports

20 garments, ski and walking boots, trainers, or be incorporated into other products to enhance their functionality and to enable the control of associated electrical equipment, for example, computers; computer keyboards; telephones; mobile telephones; personnel data

25 organisers; computer mouse; personnel audio; global positioning systems; domestic appliances; TV/videos; hi-fi

and music systems; computer game consoles; electronic musical instruments; toys; lighting; clocks and watches; mosquito traps; personal healthcare products including heart rate and other vital sign monitors, disability and mobility aids; automotive user controls; sports equipment; 5 ski goggles; skis; crash helmets for motorcycles, scooters, bikes, snow sports, motor sports, water sports; sports braces; controls for wearable electronics; educational aids; medical applications such as bed pads and blankets; 10 medical sensors; blood and glucose monitoring sensors and personal protection devices (including alarm systems).

13  
CLAIMS

1. A flexible electric circuit comprising a metallised fabric (14) characterised in that the metal is  
5 photochemically etched to form the circuit (16).
2. A circuit as claimed in claim 1 in which the fabric is porous.
- 10 3. A circuit as claimed in claim 1 or claim 2 in which the fabric is coated with a continuous layer of metal.
4. A circuit as claimed in claim 1 or claim 2 in which the fabric comprises yarns and/or fibres, the individual  
15 yarns and/or fibres being encapsulated in metal prior to manufacture of the fabric.
5. A circuit as claimed in any one of claims 1 to 4 in which the fabric is any one of woven, non-woven, knitted, a  
20 laminated composite, pressed felt, braid.
6. A circuit as claimed in any one of claims 1 to 4 in which the fabric is woven from polyester threads and the metal is nickel.

14

7. A method of manufacturing a flexible electric circuit comprising providing a metallised fabric (14), characterised by photochemically etching the metal to form the circuit (16).





FIGURE 1





3/4





FIGURE 3



# INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 02/05632

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 H05B3/34

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 H05B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	GB 2 092 868 A (MB METALS LTD) 18 August 1982 (1982-08-18) claims 1-6; figure 1 ---	1-7
Y	GB 2 175 849 A (NICHOLLS EDWARD RICHARD) 10 December 1986 (1986-12-10) page 1, column 96-104 page 2, column 78-98 ---	1-7
A	US 5 352 862 A (BARR GEORGE A) 4 October 1994 (1994-10-04) abstract ---	1-7
A	US 4 201 825 A (EBNETH HAROLD) 6 May 1980 (1980-05-06) abstract ---	1-7
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

11 March 2003

Date of mailing of the international search report

31 MAR 2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

ERIK MILIANDER/JA A

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 02/05632

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 565 745 A (KAMINSKAS RIMVYDAS A) 21 January 1986 (1986-01-21) abstract -----	1-7

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

P /GB 02/05632

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
GB 2092868	A	18-08-1982	NONE	
GB 2175849	A	10-12-1986	NONE	
US 5352862	A	04-10-1994	CA 2090080 A1	10-05-1994
US 4201825	A	06-05-1980	DE 2743768 A1	12-04-1979
			BE 870831 A1	28-03-1979
			CA 1138271 A1	28-12-1982
			CH 618055 A ,B	15-07-1980
			ES 473747 A1	01-04-1979
			FR 2404704 A1	27-04-1979
			GB 2005310 A ,B	19-04-1979
			IE 47384 B1	07-03-1984
			IT 1099610 B	18-09-1985
			JP 54055700 A	02-05-1979
			JP 62018670 B	23-04-1987
			NL 7809823 A	02-04-1979
US 4565745	A	21-01-1986	NONE	